



# BITUMODE FLEX -Anti Root

## SBS MODIFIED BITUMEN ELASTOMERIC WATERPROOFING MEMBRANE REINFORCED WITH NON-WOVEN POLYESTER with PREVENTOL B2

TECHNICAL DATA		UNIT	RESULT			TOLER.	TEST METHOD	الخواص الفنية	
Product		Roll	P-180	P-200	P-250				
Roll Length		m	10			1%	EN 1848-1	الطول	
Roll Width		m	1			1%	EN 1848-1	العرض	
Thickness		mm	4.0			(- 0.2)	EN 1849-1	السك لتشطيب السطح بولى ايثلين	
Cold Flexibility		°C	-10				EN 1109	المرونة عند درجات الحرارة المنخفضة	
Heat Resistance		°C	100				EN 1110	الثبات عند درجات الحرارة العالية	
Water impermeability at 100 Kpa		-	Absolutely impermeable				EN 1928:2000	مقاومة نفاذية الماء عند 100 كيلو بسكال	
Reinforcement		g/m <sup>2</sup>	NON-WOVEN POLYESTER					التسليح	
			<b>180</b>	<b>200</b>	<b>250</b>				
Tensile Strength	Long	N/5cm	800	900	1100	-20%	EN 12311-1	طولياً	مقاومة الشد القصوى
	Wide	N/5cm	650	700	850	-20%		عرضياً	
Elongation at break	Long	%	50	50	50	-15	EN 12311-1	طولياً	الاستطالة القصوى
	Wide	%	50	50	50	-15		عرضياً	
Tear Resistance	Long	N	550	650	750	-10%	ASTM D-5147	طولياً	مقاومة التمزق طبقاً للمواصفات الأمريكية
	Wide	N	450	550	600	-10%		عرضياً	
Joint Tensile Strength	Long	N	800	900	1100	-20%	EN 12317-1	طولياً	مقاومة الشد عند اماكن الركوب
	Wide	N	650	700	850	-20%		عرضياً	
Dimensional stability	Long	%	± 0.5	± 0.3	± 0.2		EN 1107-1	طولياً	ثبات الأبعاد
	Wide	%	± 0.5	± 0.3	± 0.2			عرضياً	
Resistance to Impact		mm	700	800	900	-15%	EN 12691	مقاومة الاختراق الديناميكي	
Root Resistance after 42 days		-	The roots did not penetrate the specimen tested			-	CEN/TS 14416:2014	المقاومة الجذر بعد 42 يوماً	

### NOTES:

- SBS Modified Bitumen treated with Preventol B2 to precautionary protection of concrete surfaces against root penetration by unwanted vegetation will give the membrane full root resistant against roots penetration properties according to CEN/TS 14416:2014.

### STORAGE:

- BITUMODE membranes should be stored vertically in well closed and ventilated place not subject to direct sunlight.

### APPLICATION INSTRUCTIONS:

- BITUMODE membranes are installed by propane torch welding method, loose laid or fully bonded to the substrate depending on system requirements.
- While unloading from truck the rolls shall by no means allowed to fall or be thrown down from the truck.
- To avoid applying the membrane to corners with 90 °C angle, sand cement can't strip 5x5 cm should be executed at horizontal - vertical intersections.
- Surface to be waterproofed should be clean, dry, free from dust and smooth, in case of irregular surface a sand cement screed is recommended.
- Before laying BITUMODE membranes, surface should be primed with cold applied bituminous primer (BITUMODE Primer SB).
- Membrane is unrolled and placed in aligned position.
- Each roll should overlap the next by 10cm side laps and 15cm staggered end laps.
- Then, membrane should be re-rolled about half of its length without changing its orientation.
- Using a propane gas torch the membrane is un-rolled again slowly while applying the flame to the entire exposed lower face (For fully bonded system) -until the plastic cover film burns off and the bituminous mass starts melting, thus creating a heat weld between the membrane and the substrate.
- Then, torching of the seams takes place by heating the contact line at side and end laps by torch from above, pressing the upper membrane on to the lower one using a trowel, the torch has to be carefully used avoiding to keep the flame on the same point for too long.
- For sloping roofs start laying the membrane from the lower edge with longitudinal direction of rolls perpendicular to slope direction, side lap of next roll to be placed above the first one, etc...

### Bitumode Qatar Waterproofing Factory

New Industrial Zone, Doha, Qatar  
Tel: (+974) 44 44 2717  
Fax: (+974) 44 44 2818  
P.O. Box 39199, Doha, Qatar  
Email: [info@bitumodeqatar.com](mailto:info@bitumodeqatar.com)  
Website: [www.bitumodeqatar.com](http://www.bitumodeqatar.com)

