



# BITUMODE -P

## APP MODIFIED BITUMEN PLASTOMERIC WATERPROOFING MEMBRANE REINFORCED WITH NON-WOVEN POLYESTER

### What is Bitumode?

Produced by Bitumode Qatar Waterproofing factory, Bitumode is a line of polymer modified bitumen waterproofing membrane of the highest quality.

**Bitumode-P** is a modified by APP and APCO thus guaranteeing superior performance under various conditions.

**Bitumode-P** is reinforced with non-woven polyester which provides high mechanical properties and dimensional stability.

### Uses

**Bitumode-P APP** is a general-purpose membrane, can be applied virtually anywhere torch applied modified bitumen membranes subject to light to moderate mechanical stresses are specified and good cold flexibility features are required. **BITUMODE-P APP 180, APP 200 and APP 250** are suitable for heavy duty applications such as bridge decks and areas subject and area subject to heavy movements and stresses.

**Bitumode-P can be applied in:**

- Single layer roofing system for advanced use.
- Double layer roofing system.
- Multi-story car parks.

**BITUMODE P** with Mineral Slated Finish is recommended for exposed roofing system (Unprotected) for Non-accessible roofs or roofs subject to low traffic conditions.

### Advantages

**Bitumode-P** has been designed with special regard to providing clients with an excellent and versatile product.

Advantages of **Bitumode-P** include:

- Easy to apply (by torch).
- Highly mechanical properties.
- Absolute impermeability to water.
- Flexibility at low temperature.
- Excellent high temperature performance.
- Excellent adhesion on any surface.
- High dimensional stability.
- Environmentally friendly.
- Resistant to soil chemicals and salts up to certain limits.

### Quality Control

Bitumode Qatar Waterproofing Factory is ISO 9001:2015, ISO 45001:2018 and ISO 14001:2015 Certified. it applies a stringent quality control system utilizing its in-house laboratory. Occasional samples are analyzed by independent laboratories to ensure continued adherence to the highest standards (ASTM, EN etc.)

### Product Range

Standard thickness available include 3mm, 4mm & 5mm.

Upper surface finish choices include:

- Polyethylene Film (PE).
- Mineral Slated Grey (GY).

The nominal length of each roll is 10 meters, and the nominal width is one meter. Special specifications can be designed based on client's needs.



B  
I  
T  
U  
M  
O  
D  
E  
-  
P

N  
O  
N  
W  
O  
V  
E  
N  
P  
O  
L  
Y  
E  
S  
T  
E  
R

### Bitumode Qatar Waterproofing Factory

New Industrial Zone, Doha, Qatar

Tel: (+974) 44 44 2717

Fax: (+974) 44 44 2818

P.O. Box 39199, Doha, Qatar

Email: [info@bitumodeqatar.com](mailto:info@bitumodeqatar.com)

Website: [www.bitumodeqatar.com](http://www.bitumodeqatar.com)

MEMBER



# BITUMODE -P

## APP MODIFIED BITUMEN PLASTOMERIC WATERPROOFING MEMBRANE REINFORCED WITH NON-WOVEN POLYESTER

TECHNICAL DATA	UNIT	RESULT			TOLER.	TEST METHOD	الخواص الفنية		
<b>Product</b>	<b>Roll</b>	<b>P-180</b>	<b>P -200</b>	<b>P -250</b>					
Roll Length	m	10			1%	EN 1848-1	الطول		
Roll Width	m	1			1%	EN 1848-1	العرض		
Thickness	mm	4			(± 5 %)	EN 1849-1	السك لتشطيب السطح بولي ايثلين		
Cold Flexibility	°C	-5				EN 1109	المرونة عند درجات الحرارة المنخفضة		
Heat Resistance	°C	120				EN 1110	الثبات عند درجات الحرارة العالية		
Water impermeability at 100 Kpa	-	Absolutely impermeable				EN 1928:2000	مقاومة نفاذية الماء عند 100 كيلو بسكال		
Reinforcement	g/m <sup>2</sup>	NON-WOVEN POLYESTER					التسليح		
		<b>180</b>	<b>200</b>	<b>250</b>					
Tensile Strength	Long	N/5cm	750	850	1050	-20%	EN 12311-1	طولياً	مقاومة الشد القصوى
	Wide	N/5cm	650	700	850	-20%		عرضياً	
Elongation at break	Long	%	50	50	50	-15	EN 12311-1	طولياً	الاستطالة القصوى
	Wide	%	50	50	50	-15		عرضياً	
Tear Resistance	Long	N	550	650	750	-10%	ASTM D-5147	طولياً	مقاومة التمزق طبقاً للمواصفات الامريكية
	Wide	N	450	550	600	-10%		عرضياً	
Joint Tensile Strength	Long	N	750	850	1050	-20%	EN 12317-1	طولياً	مقاومة الشد عند اماكن الركوب
	Wide	N	650	700	850	-20%		عرضياً	
Dimensional stability	Long	%	± 0.5	± 0.3	± 0.2		EN 1107-1	طولياً	ثبات الأبعاد
	Wide	%	± 0.5	± 0.3	± 0.2			عرضياً	
Resistance to Impact	mm	700	800	900	-15%	EN 12691	مقاومة الاختراق الديناميكي		

### NOTES:

- Above results are based on 4 mm membrane.
- Products are available in 3, 4 and 5 mm for PE finish and 3,4 mm for slated finish.
- Due to constant product improvements, BITUMODE QATAR WATERPROOFING FACTORY reserves the right to change above values without prior notice.

### STORAGE:

- BITUMODE membranes should be stored vertically in well closed and ventilated place not subject to direct sunlight.
- Bitumode Membrane has a shelf life of 12 months from the date of production.

### APPLICATION INSTRUCTIONS:

- BITUMODE membranes are installed by propane torch welding method, loose laid or fully bonded to the substrate depending on system requirements.
- While unloading from truck the rolls shall by no means allowed to fall or be thrown down from the truck.
- To avoid applying the membrane to corners with 90 °C angle, sand cement can't strip 5x5 cm should be executed at horizontal - vertical intersections.
- Surface to be waterproofed should be clean, dry, free from dust and smooth, in case of irregular surface a sand cement screed is recommended.
- Before laying BITUMODE membranes, surface should be primed with cold applied bituminous primer (BITUMODE Primer SB).
- Membrane is unrolled and placed in aligned position.
- Each roll should overlap the next by 10cm side laps and 15cm staggered end laps.
- Then, membrane should be re-rolled about half of its length without changing its orientation.
- Using a propane gas torch, the membrane is un-rolled again slowly while applying the flame to the entire exposed lower face (For fully bonded system) -until the plastic cover film burns off and the bituminous mass starts melting, thus creating a heat weld between the membrane and the substrate.
- Then, torching of the seams takes place by heating the contact line at side and end laps by torch from above, pressing the upper membrane on to the lower one using a trowel, the torch has to be carefully used avoiding to keep the flame on the same point for too long.
- For sloping roofs start laying the membrane from the lower edge with longitudinal direction of rolls perpendicular to slope direction, side lap of next roll to be placed above the first one, etc

### Bitumode Qatar Waterproofing Factory

New Industrial Zone, Doha, Qatar

Tel: (+974) 44 44 2717

Fax: (+974) 44 44 2818

P.O. Box 39199, Doha, Qatar

Email: [info@bitumodeqatar.com](mailto:info@bitumodeqatar.com)

Website: [www.bitumodeqatar.com](http://www.bitumodeqatar.com)

MEMBER

