

Bitumode
Qatar
Waterproofing
Factory

BITUSELF COATING POLYUREA H FLEX

Sprayed, hot-applied Polyurea Waterproofing
Membrane

**PRODUCT DATA SHEET
BITUSELF COATING
POLYUREA H FLEX**



BITUSELF COATING POLYUREA H FLEX

(Sprayed, Hot-applied Polyurea Waterproofing membrane)

PRODUCT DESCRIPTION

Bituself Coating Polyurea H Flex is a 2-component polyurea resin, which cures very fast into an elastic membrane with crack-bridging capacity. This product can only be applied by 2-component spraying equipment. Bituself Coating Polyurea H Flex can be combined with different geotextiles to obtain on-site applied, seamless liners (Bitumode Spray liners). It can be also pigmented with aluminum particles pigments to obtain sun-reflective properties

APPLICATIONS

Waterproofing of concrete structures and bridge decks. Bituself Coating Polyurea H Flex can be completed with an additional UV-resistant coating. Roof waterproofing. Geomembrane lining for retention basins and secondary containment structures, ponds, landfills, tunnels, canals, dam reparations, etc

CERTIFICATIONS

- Fire test B2 (DIN 4102-1:1998): Ignitability when subjected to direct impingement of flame. Class B2
- **ETA:** European Technical Assessment document N° 16/149(ETAG033) – **CEmarking**

TECHNICAL DATA

INFORMATION ON THE PRODUCT BEFORE APPLICATION				
	Component A		Component B	
Chemical Description	Polyol/Polyamine		Aromatic isocyanate prepolymer	
Physical state	Liquid		Liquid	
Packaging	Metal container 193 kg 18.8 kg		Metal container 203kg 20.8 kg	
Non-volatile content (%)	Approx 100%		100 %	
Flash point	>100 °C		> 100 °C	
Colour	Dark yellow		Slightly yellow	
Density	Temp °C	Density (g/cm ³)	Temp °C	Density (g/cm ³)
	20	1.05	20	1.14
	60	1.02	60	1.10
Viscosity (approximate values Brookfield) (mPa.s)	Temp °C	Viscosity (mPa.s)	Temp °C	Viscosity (mPa.s)
	5	2400	5	2500
	10	1800	10	1800
	20	975	20	800
	30	550	30	450
	40	335	40	300
	50	230	50	200
60	170	60	120	
VOC (2004/42/CE)	< 2g/L, <0.2 % A, J		0 A, J	
A/B mixing ratio	A=1, B=1.08 by weight A=1, B=1 by volume			
Density and viscosity of the mixture	Fast polymerization. See Pot life data			
colour	Dark yellow, but component A is pigmented by addition of pigment paste (Pigment Spray) for Bituself Coating Polyurea H Flex			

VER 2 Printed April 2023

Bitumode Qatar Waterproofing Factory

New Industrial Zone, Doha, Qatar
Tel: (+974) 44 44 2717
Fax: (+974) 44 44 2818
P.O. Box 39199, Doha, Qatar
Email: info@bitumodeqatar.com
Website: www.bitumodeqatar.com





BITUSELF COATING POLYUREA H FLEX

(Sprayed, Hot-applied Polyurea Waterproofing membrane)

Pot Life	Gel time mixture A+B (20 g) 8-9 s at 25°C 4-6 s at 60°C
Storage	Keep between 10° y 30°C. Product is hygroscopic: protect from moisture. Component B may become hazy upon storage at low temperatures. Reheat <u>mildly before use</u> .
Use before	12 months after manufacture, provided it is kept in its sealed container

INFORMATION ON THE FINAL PRODUCT

Final state	Solid Elastomeric membrane			
Colour	Variable, depending on the chosen pigmentation. For colours available, please contact bitumode Also possible addition of aluminium containing pigments for sun reflection effects			
Hardness (shore)	90 A/40 D (ISO 868)			
Tear strength	69 N/mm (ISO 34-1 Method B)			
Mechanical properties	Maximum elongation: 400 % Tensile strength: 15 MPa (EN ISO 527-3)			
Static indentation	Liners obtained by combination of Bituself Coating PolyureaH Flex and selected geotextiles achieve a static indentation resistance above 3200 kN (UNE EN ISO 12236:2007)			
Adhesion strength (EN 1542)	substrate	Adhesion strength (mpa)		
	Concrete (EP 100primer)	5.6		
	Steel (PU primer)	3.6		
UV resistance	Good resistance to UV-induced degradation. Aromatic polyureas undergo change of colour under sunlight. Additional UV protection can be achieved by application of a top coat			
Fire resistance	Class B2 DIN 4102-1: 1998			
Water vapour permeability (EN ISO 7783:2012)	μ= 1534			
Abrasion resistance	Taber, CS17, 1000 c, 1kg: 25mg			
Chemical resistance	Permanent contact (7 days, 80° C 0=worst, 5= best)			
	Chemical	results	Chemical	results
	water	5	Xylene	0
	Ammonia (3%)	5	Sulphuric acid (50%)	0
	Hydrochloric acid 3M (9%)	4	Urea	5
	Isopropyl alcohol	1	Ammonium nitrate	5

SUPPORT REQUIREMENTS

In order to achieve a good penetration and bonding, support must be:

1. Flat and levelled
2. Coct and cohesive (pull off test must show a minimum resistance of 1.5N/mm2).
3. Even and regular surface
4. Free from cracks and fissures. If any, they must be previously repaired.
5. Clean and dry, free of dust, loose particles, oils, organic residues or laitance



BITUSELF COATING POLYUREA H FLEX

(Sprayed, Hot-applied Polyurea Waterproofing membrane)

RECOMMENDED ENVIRONMENTAL CONDITIONS

Air temperature should be between 10°C and 40°C. Relative air humidity should be less than 85%.

SUPPORT PREPARATION

Concrete substrates must be prepared mechanically using high pressure sand or abrasion, in order to remove the surface and obtain an open pore. Substrates must be primed and levelled until a regular surface is obtained. Sharp irregularities are eliminated using an abrading disc machine. Eliminate all dust and loose particles from the substrate by brushing or vacuum cleaning.

MIXING

Stir and homogenize separately both components using suitable mixing equipment before being loaded into the machine. Add the required pigment to the A-component and stir before loading at low speed for a few minutes. Excessive stirring may lead to undesirable moisture pick up. Recirculate both components while heating up to the required application temperatures

APPLICATION GUIDELINES

Bituself Coating Polyurea H Flex must be applied using a 2-component hot spraying equipment. Recommended temperatures are:

- Component A: 65°C
- Component B: 70°C
- Hose: 65°C

Pressure should be between 135 and 170 bar.

During application, check layer thickness and curing speed.

Spray Bituself Coating Polyurea H Flex at 2 kg/m² as a general rule.

Wind speeds in excess of 25 km/h may result in excessive loss of exotherm and interfere with the mixing efficiency of the spray gun affecting polyurea surface texture, cure, and physical properties and will cause overspray issues.

Contact Bitumode QATAR for more detailed technical information

CURING TIME

Bituself Coating Polyurea H Flex cures to touch after a few minutes after application.

Approximate hardness values are provided as reference only (1 mm, polypropylene support, 25°C 50% RH).

TIME	Hardness (Shore A/D)
10 Min	74/27
20 Min	77/29
1 hrs.	80/30
24 hrs.	88/35

RE-APPLICATION

Usually, needed thickness can be obtained in one single coat. If necessary, a second coat can be applied immediately afterwards

RETURN TO SERVICE

Under most usual conditions (25°C, 50% rh), the membrane is resistant to rain droplets after 15 minutes, and able to resist light pedestrian traffic in 1 hour. After 2 days, 90% of the final properties are reached.

TOOL CLEANING

Solvent use for machine component cleaning is discouraged. A cleaning plasticizer fluid is suitable. Component B must be completely removed from all air-exposed parts and replaced with cleaning fluid.

A maintenance work must be carried out regularly on the treated roofs according to the intended use.

This work includes the following tasks:



BITUSELF COATING POLYUREA H FLEX

(Sprayed, Hot-applied Polyurea Waterproofing membrane)

- Leaf removal
- Grass, dirt, moss and other vegetation removal
- Keeping storm water system in good working order.
- Ensure gratings are in place, in order to prevent gutter obstructions.
- Check proper condition of several structures (flashing, seams, retaining walls...)
- Verification of possible damages due to improper use.

If aesthetic appearance of the roof is an important issue, it is essential to regularly clean the surface with water (some mild detergent may be added), according to the use.
It may be necessary to reapply decorative layers if they are worn out due to traffic, weather, corrosion, etc.

For stain removal, a surface treatment with solvent or isopropyl alcohol may be attempted. Strong acids are totally inadequate. Some solvents may damage the membrane. If this happens, the affected area has to be cut and repaired with a new Bituself Coating Polyurea H Flex or Bituself application

FAQ

Problem	Question	cause	solution
Product does not cure	AB ratio is correct?	Pressure differences	Check and correct machine operation
Bubbles or open pores	Porous support?	No primer	Apply suitable primer before Bituself Coating Polyurea H Flex
No hiding power	Horizontal?	Too little product	Apply 1 kg/m ²
		Too little pigment	Ensure full A+ pigment homogeneization
Colour change	Exposed to sunlight?	UV-reaction	Use a last coat in dark grey or red
	Can it be applied without pigmentation?		Not recommended. Bituself Coating Polyurea H Flex is always delivered with the pigment of choice. Use of pigment helps to obtain a uniform appearance

SAFETY

Component B contains isocyanates. Always follow the safety instructions in the Material Safety Data Sheet. As a general rule, a good ventilation and/or respiratory protection is needed (combined organic vapor filter+particles) along with protective clothing. This product must be used only for the applications here described. This product is intended for industrial and professional use. It is not suitable for DIY-type applications

ENVIRONMENTAL PRECAUTIONS

Empty containers must be handled with the same precautions as if they were full. Treat empty containers as hazardous waste, and transfer them to an authorized waste manager. If the container still has some material left, do not mix with other product with no knowledge of potential dangerous reactions. Component A and B may be mixed on a 1/1 ratio in order to get an inert material, but never do it in volumes larger than 5 litres in order to prevent a dangerous heat evolution

OTHER INFORMATION

The information contained in this DATA SHEET, as well as our advice, both written as verbal or provided through testing, are based on our experience, and they do not constitute any product guarantee for the installer, who must consider them as simple information.

We recommend to study deeply all information provided before proceeding to the use or application of any of our products, and strongly advise to conduct tests "on-site" in order to determine their convenience for a specific project. Our recommendations do not exempt of the obligation of installers to deeply study the right application method for these systems before use, as well as to conduct as many preliminary tests as possible should any doubt arise. The application, use and processing of our products are beyond our control, and therefore under the exclusive responsibility of the installer. In consequence, the installer will be the only responsible of any damage derived from the partial or total in-observation of our indications, and in general, of the inappropriate use or application of these materials.

VER. 2 Printed April 2023

Bitumode Qatar Waterproofing Factory

New Industrial Zone, Doha, Qatar
Tel: (+974) 44 44 2717
Fax: (+974) 44 44 2818
P.O. Box 39199, Doha, Qatar
Email: info@bitumodeqatar.com
Website: www.bitumodeqatar.com

